

CLASSIFICATION

CONFIDENTIAL

CENTRAL INTELLIGENCE AGENCY

INFORMATION REPORT



U
(31)

COUNTRY Korea/USSR

DATE DISTR. 25X1A
19 Mar 1951

SUBJECT Analysis of Soviet Rubber Tourniquet

NO. OF PAGES 1

PLACE
ACQUIRED

25X1A

NO. OF ENCLS.
(LISTED BELOW)

DATE
ACQUIRED

SUPPLEMENT TO
REPORT NO.

25X1X

- Both X-ray diffraction and infra red absorption tests show that the elastomer is natural rubber.
- The major pigment loading is whiting [calcium carbonate], constituting roughly half of the weight of the compound. The identity of the loading pigment was established by X-ray diffraction. Ashing a known weight of sample gave the concentration of the whiting.
- The material showed a tensile strength of 860 lbs per square inch and an ultimate elongation of 1430%. These properties are characteristic of a distinct undercure, but this may have been intentional in order to secure a low modulus and high elongation. The tourniquet is probably quite adequate for its intended purpose.

-end-

CLASSIFICATION

CONFIDENTIAL

CONFIDENTIAL

STATE	<input checked="" type="checkbox"/>	NAVY	<input checked="" type="checkbox"/>	NSRB		DISTRIBUTION														
ARMY	<input checked="" type="checkbox"/>	AIR	<input checked="" type="checkbox"/>	FBI																